

[붙임] 경량 패딩 조끼 시험 결과표

브랜드		탐텐	유니클로	빈폴	헤지스	스파오	지오다노	폴햄	에잇세컨즈	네파	컬럼비아
제품번호		MSZ4VP1503A	311-419995	BC9838A115	HZJU9D405	SPJV949C01-01	01-07-9908	PHA5VP1001A	429838LY15-090	7F51301	CZ4YMM191
											
표시가격(원) ¹⁾		59,900	49,900	168,000	159,000	39,900	59,800	69,900	49,900	109,000	149,000
서멀마네킹 보온성 측정(clo)		0.110	0.123	0.129	0.148	0.110	0.123	0.110	0.116	0.116	0.135
중량(g)		164.87	150.84	289.70	238.04	178.20	149.90	143.30	137.37	187.63	265.05
다운중량(g)		42.9	30.2	30.4	35.2	56.0	54.8	42.9	41.6	36.8	62.0
충전재의 품질	조성혼합률 (숨털, %)	81. 2	90.5	90.8	90.4	80.6	90.3	81.3	82.7	83.7	81.1
	충전성 (mm/30g)	136	153	136	136	123	166	152	140	161	122
	우모혼합률 ²⁾ (거위, %)	93.2	-	91.5	91.0	-	-	90.8	-	81.4	84.0
	탁도(mm)	300이상	300이상	300이상	300이상	300이상	300이상	300이상	300이상	300이상	300이상
	냄새	합격	합격	합격	합격	합격	합격	합격	합격	합격	합격

1) 택의 표시 가격

2) 충전재에 '거위'로 표시한 제품만 대상

- 일광견뢰도, 땀.일광견뢰도, 마찰견뢰도는 한국소비자원 권장품질규격 충족
- 드라이클리닝견뢰도, 물견뢰도, 세탁치수변화율은 한국소비자원 권장품질규격 충족, 세탁 후 외관은 만족스러움
- 안전성 검사 결과 아릴아민, 폼알데하이드, 유기주석화합물은 검출되지 않았고, pH는 안전기준 부속서1 가정용 섬유제품의 기준 이내